



NATURAL DESIGN



Mixed Sources

Product group from well-managed forests and other controlled sources
www.fsc.org Cert no. SGS-COC-24310
© 1996 Forest Stewardship Council

Z-Offset W

200 gsm

- Upon request available in FSC quality and CO₂ neutral

Properties

Top-quality, ecologically adjusted, natural shade creative offset paper as an alternative to extra-white offset papers. The W in the name means it helps preserve our woods and forests.

Z-Offset W sets new standards in the graphics industry with its elegant natural shading, premium quality and low environmental impact. It provides perfect offset quality and a pleasant colour tone. In addition, Z-Offset W and Z-Copy W can be combined ideally together. Companies that attach importance to ecological considerations in respect of their corporate image and therefore aim to build their corporate identity on natural white paper need look no further than Z-Offset W for the ideal solution. Z-Offset W is therefore frequently used as a creative paper.

Applications

- Offset printability ****
- Laser Printer (reels) -
- Ink-Jet *
- Copier (mono) -
- Copier (color) -
- Thermal transfer -
- Flexo Print ****
- Hand writing pen / Nylon tip **

Special features

- greetings cards

Special approvals

Features

- chlorine free
- constant high-grade quality
- high opacity
- natural white tone
- no added brighteners

Special norms fulfilled

Quality assurance system	ISO 9001:2000
Aging properties	ANSI/NISO Z.39.48-1992, ISO 9706-1994, DIN 6738-1992
Others	BfR XXXVI (analysis for the conformity with the demands on food contact materials)

Environment programs

Forest certifications: ISO 14000, EMAS or FSC	ISO 14000, EMAS or FSC
Environmental quality system	ISO 14001:2004, FSC-SQS-COC-24310
Pulp Quality	ECF/TCF-mix woodfree, FSC mixed sources
Sizing	acid-free, neutral sizing

Physical properties

	Value	Control methods
Grammage	200 ± 3	ISO 536
Smoothness (Parker Print-Surf)	5.25 ± 0,25	ISO 8791/4
Brightness	88 ± 1,5	DIN 53145
Ash content	6,5 ± 1,0	ISO 2144
Opacity	97 value as experience shows	DIN 53146
Surface pH-Value	7,3 ± 0,5	SVI-EMPA 12
Relative humidity	45 ± 5	ISO 287

User tips

Temperature	20 ± 3 °C
Relative humidity	50 ± 5 %

Processing

Adhesive laminating	*
Aluminium laminating	-

Legende

****super ***excellent **good *adequate -no information

Subject to modification at any time resulting from technical improvement. Status: 03.2010



www.zieglerpapier.com