

# Z-Offset | Z-Mail Supra 120 gsm



- Upon request available in FSC quality and CO<sub>2</sub> neutral

## Properties

Super-white offset paper for demanding applications. 110 gsm for outdoor posters.

Z-Offset is renowned for its consistently high level of quality, whiteness, opacity and bulk. Accurate cutting and a precise surface structure guarantee outstanding processing on all offset printing machines. The same paper is designated Z-Mail Supra, is perfect for conversion into envelopes due to excellent sizing, superior printability and high level of opacity. All weights in White-Line are the same shade so it is always possible to combine content and envelope for a perfect match. Z-Offset in 300 and 400 gsm weights is bonded.

## Application

- Offset printability \*\*\*\*
- Laser Printer (reels) -
- Ink-Jet \*
- Copier (mono) -
- Copier (color) -
- Thermal transfer -
- Flexo Print \*\*\*\*
- Hand writing pen / Nylon tip \*\*

## Special features

- envelope paper
- drawing paper

## Special approvals

## Features

- constant high-grade quality
- high brightness
- high opacity
- high volume

## Special norms fulfilled

Quality assurance system/Security system  
Aging properties  
Others

ISO 9001:2008/18001:2007  
ANSI/NISO Z.39.48-1992, ISO 9706-1994, DIN 6738-1992  
BfR XXXVI (analysis for the conformity with the demands on food contact materials)

## Environment programs

Forest certifications:  
Environmental quality system  
Pulp Quality  
Sizing

ISO 14000, FSC 024310  
ISO 14001:2004, FSC-SQS-COC-024310, EMAS  
ECF/TCF pulp, woodfree  
acid-free, neutral sizing

## Physical properties

Grammage  
Thickness  
Smoothness (Parker Print-Surf)  
Brightness  
CIE-Whiteness

Opacity  
Ash content  
Surface pH-Value  
Relative humidity

	Value	Control methods
Grammage	120 ± 2	ISO 536
Thickness	160 ± 5	ISO 534
Smoothness (Parker Print-Surf)	5,50 ± 0,5	ISO 8791/4
Brightness	111,5 ± 1	DIN 53145
CIE-Whiteness	165 value as experience shows	ISO 11475
Opacity	> 98	DIN 53146
Ash content	12 ± 1	ISO 2144
Surface pH-Value	7,3 ± 0,5	SVI-EMPA 12
Relative humidity	45 ± 5	ISO 287

## User tips

Temperature 20 ± 3 °C  
Relative humidity 50 ± 5 %

## Processing

Adhesive laminating \*\*  
Aluminium laminating \*

### Legende

\*\*\*\*super \*\*\*excellent \*\*good \*adequate -no information