



Z-Release Mono | Release Liner | Base Paper 120 gsm

- Available in FSC quality and CO₂-neutral on request.

Properties

This is a release liner for use in the areas of labels, adhesive tapes, sign vinyls, plotters, digital printing and carbon fibre substrates. Z-Release Mono is a coated release liner that is available in weights from 80 to 135 gsm. The special coating ensures good dimensional stability and lay-flat behaviour in all areas of application.

Z-Release Duo is a release liner coated on both sides for applications where good holdout properties are especially important. Both sides are excellent for coating with silicone. Z-Release Duo is supplied in 80 and 120 gsm.

All Specialties papers are woodfree and acid free, have neutral sizing and excellent aging properties.

Application

- Solvent-free silicone systems ****
- Solvent-based silicone systems **
- Electron-beam-curable silicone systems -
- UV-curable silicone systems ****
- Emulsion silicone systems ***

Special features

- Sign & digital printing for advertising on motor vehicles and for peel-off signs in the trade-fair and contract sectors
- Backing paper for PSA labels and films of all kinds

Features

- Very good silicone adhesion and low silicone consumption
- Excellent dimensional stability even with severe climatic fluctuations
- Good blister resistance even on high-temperature substrates
- Very good reel quality
- Individual support and personal consultation

Special standards

Quality assurance system/safety system	ISO 9001:2008/OHSAS 18001:2007
Environmental quality system	ISO 14001:2004
Pulp quality	FSC-COC-024310; ECF / TCF, woodfree
Others	BfR XXXVI (analysis for conformity with the demands on food contact materials)

Physical properties

	Value	Control methods	
Grammage	gsm	120 ± 3	ISO 536
Thickness	µm	117 ± 5	ISO 534
Smoothness (Bekk) top side	sec	> 150	ISO 53107
Smoothness (Bekk) rear side	sec	> 80	ISO 53107
Brightness	%	85	DIN 53145
Absolute humidity	%	ca. 4	
Tensile strength md	kN/m	> 8.8	DIN EN 1924-2
Tensile strength cd	kN/m	> 5.4	DIN EN 1924-2
Cobb Rizinus (2 min) top side	gsm	< 1.5	
Cobb Rizinus (2 min) rear side	gsm	< 3.5	

User tips

Do not unpack reels until immediately before processing. Avoid storing opened reels where humidity conditions are high.

Legend

****super ***excellent **good *adequate -no information

Subject to modification at any time resulting from technical improvement. Status: 09.2011